



# NEODUR NVP Trass/HS

## natural stone injection mortar

**FOR INJECTION AND FILLING OF GAPS IN NATURAL STONE MASONRY ON THE BASIS OF TRASS WITH HIGH SULPHATE RESISTANCE**

### DESCRIPTION

NEODUR natural stone injection mortar NVP Trass/HS is a factory-produced, ready to use, building physical adapted injection mortar for the filling of natural stone masonry.

### APPLICATION

NEODUR NVP Trass/HS is used for the filling of gaps, backfill and injection works as well as for the consolidation of any kind of natural stone masonry, indoors and outdoors.

### PROPERTIES

- pumpable
- low viscosity
- chloride-free
- building physics adapted to natural stone

### TECHNICAL DATA

**Raw material basis:** Special binding agent with high sulphate resistance acc. to DIN EN 197-1/DIN 1164, Trass acc. to DIN 51043 and specially selected mineral fillers.

**Grain size:** flour grain  
**Water addition per unit:** approx. 8 ltr

**Mixing time:** approx. 3 min  
**Yield per unit:** approx. 16 ltr  
**Processing temperature:** > 5° C  
**Mortar group:** MG II-III  
**Swelling index:** > 0,1 vol. %

### PROCESSING

NEODUR natural stone injection mortar NVP Trass/HS to be mixed in pan type mixer as complete unit with approx. 8 ltr water. Then fill gaps with suitable injection pump. Differing temperatures may influence the stiffening resp. hardening procedure.

### PRODUCTION

KORODUR Westphal Hartbeton GmbH & Co. works Wattenscheid

**Certification:** DIN EN ISO 9001:2000

### PACKAGING/ SUPPLY

20 kg special paper packaging

### STORAGE

Dry, like cement.  
Shelf-life approx. 6 months.

### HINTS

This product contains cement and has an alkaline reaction with moisture/water. Therefore protect hands and eyes. In case of contact with eyes consult a doctor. Our recommendations for application techniques are based on our experiences. It is recommended to adapt processing and material quantities to the given local conditions and we refer in this context to our AGB. Further literature, processing hints, tender texts and test certificates on the different KORODUR industrial flooring systems, KORODUR floor hardeners, KORODUR dry mortars and special products are available on request.



**KORODUR International GmbH** [www.korodur.de](http://www.korodur.de)

**Zentrale:**  
Wernher-von-Braun-Str. 4  
92224 Amberg  
Postfach 1653 • 92206 Amberg  
Tél.: +49 (0) 96 21 / 47 59-0  
Fax: +49 (0) 96 21 / 3 23 41  
info@korodur.de

**Werk Bochum-Wattenscheid:**  
Hohensteinstr. 19  
44866 Bochum  
Postfach 60 02 48 • 44842 Bochum  
Tél.: +49 (0) 23 27 / 94 57-0  
Fax: +49 (0) 23 27 / 32 10 84  
wattenscheid@korodur.de

