

Tender Specification Rapid Set TRU Self-Leveling			
One-layer, self-leveling design floor TRU Self-Leveling			
In composite on base concrete / screed			
Project name : Project no :			
TRU Self-Leveling Layer thickness 4 to 35 mm			
color:			
item	performance / product	per unit	total
		€/m²	€
	 Pre treatment of the base concrete / screed by shot-peening or similar, high pressure water cleaning and vacuum treatment. The sub-base must meet the requirements of DIN 18365 as well as DIN 18660 part 3, line 4.1 (compressive strength > 30 N/m², bond strength 1,5 N/m²). Joints in the sub-base have to be taken over in the topping layer. Application of epoxy primer KORODUR TXPK (min. 400 g/m²) including sprinkling with fire-dried quartz sand, grain size 0,4 - 0,8 mm. In given case embedding of a fabric. For further information see the data sheet Epoxy primer KORODUR TXPK. TRU Self-Leveling mm thick, in flowable consistency (admixture of water 4,11 per 22,7 kg bag). To be applied and spread on the primer within the 15 minutes working time. For further information see the data sheet TRU Self-Leveling. Processing temperature min. + 10 °C, max. + 25 °C. Manufacturer's instructions to be observed. Consumption per m², per mm layer thickness in middle 1,7 kg. Individual optics can be produced by admixture of pigments or decorative aggregates. Further details as described below: 	€/M ²	
LV Rapid	Set TRU Self-Leveling / 130317		